

## Product Data Sheet

### 100mic Milk White Electrostatic PVC Film

#### Description

##### Face material:

100mic milk white electrostatic PVC film

##### liner:

135gsm white liner

#### Typical value

|                             |                                                             |            |
|-----------------------------|-------------------------------------------------------------|------------|
| Thickness<br>(Face film)    | 110±12mic                                                   | (ISO 4593) |
| Weight<br>(Face film)       | 150±16g/m <sup>2</sup>                                      | (ISO 536)  |
| Hardness<br>(Face film)     | 83±3A                                                       | (ISO 868)  |
| Thickness<br>(liner)        | 170±15mic                                                   | (ISO 534)  |
| Weight<br>(liner)           | 136±10g/m <sup>2</sup>                                      | (ISO 536)  |
| Whiteness<br>(liner)        | ≥90%                                                        | (ISO2470)  |
| Available<br>Lengths&Widths | Custom sheet sizes available<br>Roll width: 100mm to 1070mm |            |

#### Application

Better electrostatic adsorption capacity, mostly used on very smooth surfaces such as glass, lenses, metals, etc.

#### Printing Methods

Good surface adhesion performance, commonly used on offset printing, letterpress printing, and low temperature screen printing, etc., has a strong ink absorption effect.

#### Storage

Storage relative humidity: 55 ± 5%  
Storage temperature: 23±5℃  
Storage time: 12 months

#### Attention

The application humidity range is 45% to 55%. Beyond this humidity range, customers are advised to use it after testing. Surfaces to be applied must be cleaned thoroughly of dust, grease or any contaminants. This information is based upon our knowledge and practical experience but does not constitute a warranty. All information is subject to change without prior notice.