

Product Data Sheet

Self Adhesive 60mic Glossy White PP Film

Description

Face material:

60mic glossy white PP film

Adhesive:

Hot melt pressure sensitive adhesive, can be used on a variety of substrates over a wide temperature range.

Liner:

30mic transparent PET release film

Typical value

Thickness (Face film)	60±5mic	(ISO 534)
Weight (Face film)	48±6g/m ²	(ISO 536)
Thickness (Adhesive)	20±3mic	(ISO 2808)
Thickness (Release paper)	34±6mic	(ISO 534)
Weight (Release paper)	47±7g/m ²	(ISO 536)
Loop Tack	≥18N/25mm	(FTM9 on stainless steel)
Peel Adhesion	≥10N/25mm CF	(FTM1 on stainless steel)
Shear Adhesion	>2h	(FTM8 on stainless steel)
Service temperature	Min.Appl.Temp: 5℃ Service Temp: -20 ~ 60℃	
Available Lengths&Widths	Custom sheet sizes available Roll width: 100mm to 1080mm	

Attention

The application humidity range is 45% to 55%. Beyond this humidity range, customers are advised to use it after testing. Surfaces to be applied must be cleaned thoroughly of dust, grease or any contaminants. This information is based upon our knowledge and practical experience but does not constitute a warranty. All information is subject to change without prior notice.

Application

This product is suitable for a variety of promotional and industrial label applications. Typical applications include labeling systems for the cosmetics, pharmaceutical, and food industries.

Printing Methods

Suitable for flexo, letterpress- uv, screen printing and offset. For best ink recommendations, please contact your ink supplier. Testing for suitability of media, printers and inks is always recommended prior to use.

Storage

Storage relative humidity: 50±5%
Storage temperature: 23±2℃
Storage time: 12 months

Shanghai RIGHTINT Self Adhesive New Material CO., LTD

ADD: Room 616-617, Qibao International Building No.96, Lane 1333 XinLong Road, Minhang District, Shanghai

TEL:+86-021-36530656 Web: www.rightint.com