

Product Data Sheet

200mic Matt PP Synthetic Paper

Description

Material:

200mic matt PP synthetic paper (coated two sides)

Typical value

Thickness	205±5mic	(ISO 534)
Weight	140±5g/m ²	(ISO 536)
Whiteness	95±5%	(ISO 2470)
Surface Tension Strength	S1.S2 ≥ 40Dyn/cm	(ISO 8296)
Tensile strength	MD ≥ 30Mpa CD ≥ 80Mpa	(ISO 527)
Elongation at Break	MD ≤ 200% CD ≤ 100%	(ISO 527)
Available Lengths&Widths	Custom sheet sizes available Roll width: 950mm to 1090mm	

Application

High quality face material, can be widely used in tags, tickets, business leaflets, daily chemical, food, beverage and electronics industries.

Printing Methods

This product is suitable for flexo, letterpress, offset printing, screen printing, while for other printing methods, testing for the suitability of printers and ink/toner is always recommended prior to use.

Storage

Storage relative humidity: 50±5%
Storage temperature: 23±2°C
Storage time: 12 months

Attention

The application humidity range is 45% to 55%. Beyond this humidity range, customers are advised to use it after testing. Surfaces to be applied must be cleaned thoroughly of dust, grease or any contaminants. This information is based upon our knowledge and practical experience but does not constitute a warranty. All information is subject to change without prior notice.

Shanghai RIGHTINT Self Adhesive New Material CO., LTD

ADD: Room 616-617, Qibao International Building No.96, Lane 1333 XinLong Road, Minhang District,
Shanghai

TEL: +86-021-36530656 Web: www.rightint.com